

IN THE CLAIMS:

Claims 1-7 (canceled).

Claim 8 (currently amended) An ink composition comprising a pigment, a polymer emulsion comprising fine particles of a polymer, water, a solid wetting agent and a water-soluble organic solvent, said solid wetting agent being selected from the group consisting of hyaluronic acid, trimethylolpropane and 1, 2, 6- hexanetriol,

said polymer emulsion being produced by a process which comprises the steps of:

mixing water, a monomer, an emulsifier, and a polymerization initiator together to allow emulsion polymerization to proceed with formation of a resultant polymer emulsion; and

adjusting the pH of the resultant polymer emulsion to neutral or alkaline by adding a monovalent inorganic hydroxide.

Claim 9 (original) The ink composition according to claim 8, wherein the content of the fine particles of the polymer constituting the polymer emulsion is 0.01 to 30% by weight based on the total amount of the ink composition.

Claim 10 (original) The ink composition according to claim 8, wherein the pigment has on its surface a hydrophilic group.

Claim 11 (original) The ink composition according to claim 10, wherein the pigment having on its surface a hydrophilic group is carbon black or an organic pigment.

Claim 12 (previously presented) The ink composition according to claim 10, wherein the hydrophilic group present on the surface of the pigment is a sulfonic acid ( $-\text{SO}_2\text{OH}$ ) and/or a sulfinic acid group  $-\text{RSO}_2\text{H}$ , wherein R represents a  $\text{C}_1$  to  $\text{C}_{12}$  alkyl group or a phenyl group or a derivative thereof.

Claim 13 (previously presented) The ink composition according to claim 10, wherein the hydrophilic group present on the surface of the pigment is a sulfonic acid anion group ( $-\text{SO}_3^-$ ) and/or a sulfinic acid anion group  $-\text{RSO}_2^-$ , wherein R represents a  $\text{C}_1$  to  $\text{C}_{12}$  alkyl group or a phenyl group or a derivative thereof.

Claim 14 (original) The ink composition according to claim 10, wherein the hydrophilic group present on particles of the pigment is a carboxylic acid group ( $-\text{CO}_2\text{H}$ ) and/or a carboxylic acid anion group ( $-\text{CO}_2^-$ ).

Claim 15 (currently amended) The ink composition according to claim 8, which further comprises a penetrating agent or a wetting agent.

Claim 16 (original) The ink composition according to claim 15, wherein the penetrating agent is one or more members selected from the group consisting of 1, 2-alkyl diols, glycol ethers, acetylene glycol surfactants, and acetylene alcohol surfactants.

Claim 17 (original) The ink composition according to claim 16, wherein the 1, 2-alkyl diol is 1, 2-hexanediol or 1,2-pentanediol.

Claim 18 (original) The ink composition according to claim 16, wherein the glycol ether is one or more members selected from the group consisting of dialkylene glycol monobutyl ethers, dialkylene glycol monopentyl ethers, dialkylene glycol monohexyl ethers, trialkylene glycol monobutyl ethers, trialkylene glycol monopentyl ethers, trialkylene glycol monohexyl ethers, tetraalkylene glycol monobutyl ethers, tetraalkylene glycol monopentyl ethers, and tetraalkylene glycol monohexyl ethers.

Claim 19 (currently amended) The ink composition according to claim 15, further comprising glycerin or trimethylene glycol.

Claim 20 (currently amended) The ink composition according to claim 19, wherein the content of glycerin or trimethylene glycol is 10 to 20% by weight based on the total amount of the ink composition.

Claim 21 (cancelled)

Claim 22 (currently amended) The ink composition according to claim ~~8~~ 21, wherein the content of the solid wetting agent is 3 to 20% by weight based on the total amount of the ink composition.

Claims 23 and 24 (cancelled)

Claim 25 (original) The ink composition according to claim 8, which further comprises, as a pH adjustor, one or more members selected from the group consisting of potassium hydroxide, sodium hydroxide, and lithium hydroxide.

Claim 26 (previously presented) A recording method comprising the step of: depositing an ink composition onto a recording medium to perform printing, said ink composition being one according to claim 8.

Claim 27 (original) The recording method according to claim 26, which is an ink jet recording method comprising the steps of: ejecting droplets of an ink composition; and depositing the droplets onto a recording medium to perform printing.

Claim 28 (original) A record printed by the recording method according to claim 27.

Claim 29 (previously presented) The composition according to claim 8, wherein the monovalent inorganic hydroxide is an alkali metal hydroxide.

Claim 30 (previously presented) The composition according to claim 29, wherein the alkali metal hydroxide is one member or a mixture of two or more members selected from the group consisting of lithium hydroxide, sodium hydroxide, and potassium hydroxide.

Claim 31 (previously presented) The composition according to claim 8, wherein the pH value is adjusted to 7 to 9.

Claim 32 (previously presented) The composition according to claim 8, wherein the fine particles of the polymer contain 1 to 10% by weight of a structure derived from a carboxyl-containing unsaturated vinyl monomer, have a structure which is crosslinked by a crosslinkable monomer having two or more polymerizable double bonds, and contain 0.2 to 4% by weight of the structure derived from the crosslinkable monomer.

Claim 33 (previously presented) The composition according to claim 8, wherein the fine particles of the polymer have a film-forming property, have on its surface a carboxyl group, and have a reactivity with a divalent metal salt such that, when 3 volumes of a polymer emulsion containing 0.1% by weight of the fine particles of the polymer is brought into contact with one volume of a 1 mol/liter aqueous divalent metal salt solution, the time required for the transmittance of light having a wavelength of 700 nm to become 50% of the initial transmittance value is not more than  $1 \times 10^4$  sec.

Claim 34 (previously presented) The ink composition according to claim 8, wherein the pigment is present in an amount of about 1 to 15% by weight, the water-soluble organic solvent is present in an amount of about 0.1 to 40% by weight; the fine particles of a polymer are present in an amount of about 0.1 to 30% by weight and the solid wetting agent is present in an amount between 3 to 20% by weight that is effective to provide the ink composition with an improved storage stability or anti-clogging property as compared with the ink composition without the solid wetting agent.

Claim 35 (previously presented) The ink composition according to claim 34, wherein the solid wetting agent is selected from the group consisting of a saccharide, a sugar alcohol, a salt of hyaluronic acid, trimethylolpropane, 1,2,6-hexanetriol and mixtures thereof.